



**WASHINGTON COUNTY DIVISION OF PUBLIC WORKS  
CAPITAL PROJECTS ENGINEERING**

80 West Baltimore Street  
Hagerstown, Maryland 21740-6003  
Telephone: (240) 313-2400 FAX: (240) 313-2401  
TDD / Hearing Impaired: 711

**ADDENDUM NO. 2**

TO: Interested Parties

FROM: Vicky L. McKenzie,  
Project Manager, DPW - Capital Projects Engineering

DATE: Friday, May 1, 2009

RE: Pavement Maintenance & Rehabilitation Program – FY-'10  
Chip Seal Applications  
Contract No. MS-PMP-132-28

Acknowledge receipt of this **Addendum No. 2** by signing in the space provided below and returning with your Bid.

Failure to sign and return with your Bid may subject the Bidder to disqualification. This **Addendum No. 2** forms a part of the Bid Documents, it supplements and modifies them as outlined herein.

This **Addendum No. 2** consists of 4 pages, including this page and attachments.

I hereby acknowledge receipt of **Addendum No. 2**:

By: \_\_\_\_\_  
Signed Name

Date \_\_\_\_\_

\_\_\_\_\_  
Typed Name

\_\_\_\_\_  
Title

For: \_\_\_\_\_  
Firm


**ADDENDUM NO. 3**

**Pavement Maintenance & Rehabilitation Program – FY-'10  
Chip Seal Applications  
Contract No. MS-PMP-132-28**

Date Issued: May 1, 2009


Bids Due: May 6, 2009  
2:30 p.m.

The following addendum material is hereby made a part of the Bid Documents. Please note the following changes, information, and/or instructions in connection with the proposed work and submit proposals accordingly.



*FOR* Vicky L. McKenzie,  
Project Manager,  
DPW-Capital Projects Engineering

By Authority of:  
Board of County Commissioners  
Washington County, Maryland



Robert Slocum, P.E.  
Deputy Director of Public Works  
Capital Projects Engineering

**To:** All prime Contractors and all others to whom specifications have been issued.

**Item 2.01** **SPECIAL PROVISIONS, Item No. 501 - SINGLE CHIP SEAL & Item No. 502 - DOUBLE CHIP SEAL, .02 MATERIALS, Page SP-6**

**DELETE** Table 5.1 in its entirety

**REPLACE** with Revised Table 5.1

**Attachment No. 1: SPECIAL PROVISIONS, Revised Page SP-6**

**Attachments:**

Attachment No. 1: SPECIAL PROVISIONS, Revised Page SP-6

**END ADDENDUM No. 2**

**Item No. 501 – SINGLE CHIP SEAL SURFACE TREATMENT**

**Item No. 502 - DOUBLE CHIP SEAL SURFACE TREATMENT**

**.01 DESCRIPTION:** This work shall consist of all labor, supervision, material, equipment and services necessary and incidental for applying either one (1) seal coat (Single Surface Treatment) or two (2) seal coats (Double Surface Treatment). The Single Surface Treatment consists of one seal coat of emulsified asphalt followed by an application of aggregate using No. 10 Aggregate. The Double Surface Treatment application consists of two (2) applications of emulsion and aggregate where the first seal coat is applied and followed with No. 8 Aggregate and the second seal coat is applied followed by No. 10 aggregate. This item shall be used at locations and to the limits as identified and marked in the field, listed herein and/or as directed by the Engineer

**.02 MATERIALS:**

**2** Table 5.1

| MATERIAL            | SECTION | APPLICATION  | SIZE OR GRADE    | SPREAD RATE<br>lb/yd <sup>2</sup> | SPRAY TEMP<br>F    | SPRAY RATE FOR FIRST APPLICATION OF A DOUBLE SEAL COAT<br>gal/yd <sup>2</sup> | SPRAY RATE FOR SINGLE SEAL COAT OF OR SECOND APPLICATION OF A DOUBLE SEAL COAT<br>gal/yd <sup>2</sup> |
|---------------------|---------|--|------------------|-----------------------------------|--------------------|---|---|
| Emulsified Asphalts | 904.03  | Seal Coat  | <del>CRS-1</del> | <del>—</del>                      | 70-140             | 0.25-0.50   | <del>0.18-0.38</del>  |
|                     |         |  | CRS-2PM          | —                                 | 140-160            | 0.25-0.50   | 0.18-0.38   |
|                     |         |  | <del>R-1</del>   | <del>—</del>                      | <del>70-140</del>  | <del>0.25-0.50</del>  | <del>0.18-0.38</del>  |
|                     |         |  | <del>R-2</del>   | <del>—</del>                      | <del>140-160</del> | <del>0.25-0.50</del>  | <del>0.18-0.38</del>  |
| Aggregate           | 901     | First application of a Double Seal Coat                      | No. 8            | 15-30                             | —                  | —   | —   |
|                     |         | Single Seal Coat or Second application of a Double Seal Coat | No. 10           | 10-25                             | —                  | —   | —   |

A. Wash test results shall be required on all chip seal aggregates. All aggregate specified for chip seal shall not exceed 1.0% of the material passing through the No. 200 washed sieve in accordance with test method MSMT T-11.